



# Pro-fax 6323

LyondellBasell Industries - Polypropylene Homopolymer

Wednesday, January 29, 2020

## General Information

### Product Description

Pro-fax 6323 general purpose polypropylene homopolymer is available in pellet form. This resin is typically used in injection molding applications.

An ASTM and ISO-based versions of the technical datasheet are available for Pro-fax 6323.

For regulatory compliance information see Pro-fax 6323 Product Stewardship Bulletin (PSB).

### General

Material Status	• Commercial: Active		
Regional Availability	• North America		
Features	• Good Stiffness • Heat Aging Resistant	• High ESCR (Stress Crack Resist.) • Homopolymer	
Uses	• Automotive Applications • Caps	• Closures • Containers	• Sporting Goods • Toys
Agency Ratings	• EC 1907/2006 (REACH)		
Automotive Specifications	• CHRYSLER MS-DB-500 CPN2571		
Forms	• Pellets		
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity			
--	0.900	0.900	ASTM D792B
--	0.900 g/cm <sup>3</sup>	0.900 g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12 g/10 min	12 g/10 min	ASTM D1238
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength			
Yield <sup>2</sup>	4930 psi	34.0 MPa	ASTM D638
Yield, 73°F (23°C)	4500 psi	31.0 MPa	ISO 527-2
Tensile Elongation			
Yield	11 %	11 %	ASTM D638
Yield, 73°F (23°C)	11 %	11 %	ISO 527-2
Flexural Modulus			
1% Secant <sup>3</sup>	210000 psi	1450 MPa	ASTM D790A
73°F (23°C)	187000 psi	1290 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	2.0 ft·lb/in <sup>2</sup>	4.2 kJ/m <sup>2</sup>	ISO 179
Notched Izod Impact			
73°F (23°C)	0.60 ft·lb/in	32 J/m	ASTM D256A
73°F (23°C)	2.0 ft·lb/in <sup>2</sup>	4.1 kJ/m <sup>2</sup>	ISO 180

Copyright ©, 2020 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

# Pro-fax 6323

## LyondellBasell Industries - Polypropylene Homopolymer

Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	199 °F	93.0 °C	ASTM D648
66 psi (0.45 MPa), Unannealed	169 °F	76.0 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	120 °F	49.0 °C	ISO 75-2/A

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 2.0 in/min (50 mm/min)

<sup>3</sup> 0.051 in/min (1.3 mm/min)